



## Foamspecification 1.25.\*\*R20 H

Tests	Methods*:	Units	Specification	
			Min.	Max.
Density	ISO 845	kg/m <sup>3</sup>	20,0	26,0
Compression load deflection	ISO 3386/1	kPa	3,5	6,5
Tensile strength	ISO 1798	kPa	50	
Elongation at break	ISO 1798	%	90	
Cell-count	CAL I 127.29	1/CM	4	5,5

\* Caligen testmethods are based on the mentioned (ISO) standards.

01/2001

Caligen Europe bv

Konijnenberg 59 P.O. Box 2154 NL 4800 CD Breda The Netherlands. T +31 (0)76 5780300 F +31 (0)76 58703051

[www.caligen.com](http://www.caligen.com)

[sales@caligen.com](mailto:sales@caligen.com)